

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 July 2001 (12.07.2001)

PCT

(10) International Publication Number
WO 01/49507 A1

(51) International Patent Classification⁷: B41M 5/20, 5/24

(21) International Application Number: PCT/US00/34473

(22) International Filing Date:

19 December 2000 (19.12.2000)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/174,396

5 January 2000 (05.01.2000) US

(71) Applicant: APPLETON PAPERS INC. [US/US]; 825 E. Wisconsin Avenue, P.O. Box 359, Appleton, WI 54912-0359 (US).

Street, Appleton, WI 54911 (US). JUSTA MACNEIL, Stacey, Ann; 1120 W. Harris Street, Appleton, WI 54914 (US). BERGGREN, Debra, Arlene; 730 S. John Street, Apartment #3, Kimberly, WI 54136 (US).

(74) Agent: MIELIULIS, Benjamin; Appleton Papers Inc., Law Department, 1400 N. Rankin Street, P.O. Box 359, Appleton, WI 54912-0359 (US).

(81) Designated States (*national*): AU, CA, JP.

(84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).



Published:

- With international search report.
- With amended claims.

(72) Inventors: MATHIAPARANAM, Ponnampalam; 37 Diane Lane, Appleton, WI 54915-7203 (US). DEBRAAL, John, Charles; W2437 Greenspire Way, Appleton, WI 54915 (US). FISHER, Mark, Robert; 322 N. Oneida

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: THERMALLY-RESPONSIVE RECORD MATERIAL



(57) Abstract: The present invention is a novel thermally-responsive record material comprising a substrate having provided thereon in substantially contiguous relationship an electron donating dye precursor, an acidic developer material, a compound of formula (I) wherein P is selected from (II) and (III), wherein R₁, R₂ and R₃ are independently selected from

hydrogen, alkyl, alkoxy, aryl, aralkyl, aralkoxy, halogen, and alkoxyalkoxy; wherein R₄ is independently selected from alkoxyalkyl, alkoxyalkoxy, and aralkoxyalkoxy, and a suitable binder therefor. In the context of the present invention the alkyl moieties in the alkyl, aralkyl, aralkoxy, alkoxyalkyl, alkoxyalkoxy and aralkoxyalkoxy preferably are eight carbons or less, and more preferably from one through four carbons. Substituents on aryl moieties in aryl, aralkyl, aralkoxy, and alkoxyalkoxy groups can include hydrogen, alkyl, alkoxy and halogen. The alkyl group in these substituents also is eight carbons or less, and more preferably from one through four carbons. The thermally responsive record material of the invention has the unexpected and remarkable properties of enhanced image intensity or density, and/or improved thermal response.

WO 01/49507 A1

THERMALLY-RESPONSIVE RECORD MATERIAL

5

BACKGROUND OF THE INVENTION

1. Field of the Invention.

This invention relates to thermally-responsive record material. It more particularly relates to such record material in the form of sheets or rolls coated with color-forming material comprising chromogenic material (electron-donating dye precursor) and acidic color developer material. This invention particularly concerns a thermally-responsive record material (thermal record material) capable of forming a non-reversible image resistant to fade or erasure. The invention teaches record materials having improved thermal response, image formation, image retention and/or image density.

2. Description of Related Art.

Thermally-responsive record material systems are well known in the art and are described in many patents, for example U.S. Patent Nos. 3,539,375; 3,674,535; 3,746,675; 4,151,748, 4,181,771; 4,246,318; and 4,470,057 which are hereby incorporated by reference. In these systems, basic chromogenic material and acidic color developer material are contained in a coating on a substrate which, when heated to a suitable temperature, melts or softens to permit the said materials to react, thereby producing a colored mark.

Thermally-responsive record materials have characteristic thermal responses, desirably producing a colored image upon selective thermal exposure.

In the field of thermally-responsive record material, thermal response is defined as the temperature at which a thermally-responsive material produces a colored image of sufficient intensity or density. The desired temperature of imaging varies with type of application of the thermally-responsive product and the equipment used in the imaging process. The ability to shift the temperature at which thermal image of sufficient intensity or density is produced for any given combination of chromogenic material and developer materials is a much sought after and very


valuable feature. For example, recent advances in high speed text or image recording demand both high speed recording devices and corresponding thermally-responsive recording materials with sufficient thermal response that are capable of producing a high intensity or high density color image at low thermal energy.

Also, in the field of thermally-responsive record material, the ability to increase the efficiency of the thermal image formation process has decided advantages. First among these is the ability to obtain the same image intensity or density with lower amount of reactants or, alternatively, to obtain a more intense image with the same amount of reactants.


It is an object of this invention to provide a thermally-responsive material having enhanced image intensity or density and/or improved thermal response.

DETAILED DESCRIPTION


The present invention is a novel thermally-responsive record material comprising a support having provided thereon in substantially contiguous relationship an electron donating dye precursor, an acidic developer material, a compound of the formula



wherein P is selected from



and



;


wherein R_1 , R_2 and R_3 are independently selected from hydrogen, alkyl, alkoxy, aryl, aralkyl, aralkoxy, halogen, and alkoxyalkoxy groups;

wherein R_4 is independently selected from alkoxyalkyl, alkoxyalkoxy, and aralkoxyalkoxy groups, and a suitable binder therefor;

when P is naphthalene, R_1 , R_2 and R_3 in addition to the foregoing, can also include aralkoxyalkoxy groups.


In the context of the present invention the alkyl moieties in the alkyl, aralkyl, aralkoxy, alkoxyalkyl, alkoxyalkoxy and aralkoxyalkoxy preferably are each independently eight carbons or less, and more preferably from one through four carbons. Substituents on aryl moieties in aryl, aralkyl, aralkoxy, and aralkoxyalkoxy groups can each independently include hydrogen, alkyl, alkoxy and halogen. The alkyl group in these substituents also is each independently eight carbons or less, and more preferably from one through four carbons.

More particularly, the present invention is a novel thermally-responsive record material comprising a support having provided thereon in substantially contiguous relationship an electron donating dye precursor, and acidic developer material, a compound of the formula



(II)

or



(III)

Wherein in formulas II and III, R₁, R₂ and R₃ are independently selected from hydrogen, alkyl, alkoxy, aryl, aralkyl, aralkoxy, halogen, alkoxyalkoxy, and alkoxyalkoxy groups.

Wherein in formula II and III, R₄ is independently selected from alkoxyalkyl, alkoxyalkoxy, and aralkoxyalkoxy groups, and a suitable binder therefor.

In formula III, R₁, R₂ and R₃ can in addition to the foregoing be independently selected from aralkoxyalkoxy groups.

In the context of the present invention the alkyl moieties in the alkyl, aralkyl, aralkoxy, alkoxyalkyl, alkoxyalkoxy and aralkoxyalkoxy preferably are each independently eight carbons or less, and more preferably from one through four

carbons. Substituents on aryl moieties in aryl, aralkyl, aralkoxy, and aralkoxyalkoxy groups can each independently include hydrogen, alkyl, alkoxy and halogen. The alkyl group in these substituents also is each independently eight carbons or less, and more preferably from one through four carbons.


5 The thermally responsive record material of the invention has the unexpected and remarkable properties of enhanced image intensity or density, and/or improved thermal response. The compounds disclosed herein as formula I, II or III desirably function as sensitizers or modifiers facilitating reaction between the mark forming components yielding a more intense image at lowered temperatures or faster
10 imaging.

 In the field of thermally-responsive record material, thermal sensitivity (response) is defined as the temperature at which a thermally-responsive material produces a colored image of satisfactory intensity (density). Background is defined as the amount of coloration of a thermally-responsive record material before
15 imaging and/or in the unimaged areas of an imaged material. The ability to maintain the thermal sensitivity of a thermally responsive material while reducing the background coloration is a much sought after and very valuable feature.


 These and other advantages are obtained from these compounds of the invention.

20 Increases in thermally-responsive material have been achieved through the incorporation of a sensitizing material in the color-forming composition along with the chromogenic material and acidic developer material. Examples of sensitizing materials are as follows: fatty acids such as stearic acid and behenic acid, amides of fatty acids such as stearamide, metallic salts of fatty acids such as zinc stearate,
25 aluminum stearate, calcium stearate, zinc palmitate and zinc behenate, 4-benzylbiphenyl, triphenylmethane, benzyl 4-benzoyloxybenzoate, 2-benzoyloxynaphthalene, phenyl 2-naphthoate, 1,2-diphenoxyethane, 1,2-bis (3-methylphenoxy)ethane, 1,2-bis(4-methylphenoxy)ethane, 4-hydroxyoctadecanilide. The compounds of the invention are a new class of sensitizers.

30 Compounds illustrative of the invention according to formula I, II and III include without limitation:




A




B


5




C




D




E




F




G




H




I




J




K




L




M



N




O




P

5




Q




R


10




S



T






U



V

5

In general, the compounds according to formulas I, II or III can be synthesized from a corresponding substituted or unsubstituted benzyloxyalkanol or alkoxyalkanol.



The alcohol is first converted to tosylate using p-toluenesulfonyl chloride (TsCl) and aqueous sodium hydroxide in acetonitrile, keeping the temperature of the reaction mixture below about 55°C by slow addition of the base. Then, the tosylate
5 is reacted with the corresponding phenol at 80°C for about five hours to give the final product.

The times and the temperatures in this general protocol are approximate, and the person skilled in the art can readily adjust the reaction conditions, depending on the moieties involved, to obtain the desired product.

10 More specific illustrative processes for synthesis of the specific compounds according to formulas I, II and III are set forth in more detail in synthesis example 1.

In the heat sensitive record material according to the invention, the compound according to formulas I, II or III is preferably used in an amount corresponding to 10 to 1000 parts by weight per 100 parts of the electron donating
15 dye precursor though when blended with other sensitizers, the amount of the compound according to formulas I, II or III can optionally be used in reduced amounts.

The record material includes a substrate or support material which is generally in sheet form. For purposes of this invention, sheets can be referred to as
20 support members and are understood to also mean webs, ribbons, tapes, belts, films, cards and the like. Sheets denote articles having two large surface dimensions and a comparatively small thickness dimension. The substrate or support material can be opaque, transparent or translucent and could, itself, be colored or not. The material can be fibrous including, for example, paper and
25 filamentous synthetic materials. It can be a film including, for example, cellophane and synthetic polymeric sheets cast, extruded, or otherwise formed. The gist of this invention resides in the color-forming composition coated on the substrate. The kind or type of substrate material is not critical.

The components of the color-forming system are in substantially a contiguous
30 relationship, substantially homogeneously distributed throughout the coated layer or layers of material deposited on the substrate.

The term substantially contiguous relationship is understood to mean that the color-forming components are positioned in sufficient proximity such that upon melting, softening or subliming one or more of the components, a reactive color forming contact between the components is achieved. As is readily apparent to the person of ordinary skill in this art, these reactive components accordingly can be in the same coated layer or layers, or isolated or positioned in separate layers. In other words, one component can be positioned in the first layer, and reactive or sensitizer components or the compound according to Formulas I, II or III, or an acidic developer or color former positioned in a subsequent layer or layers. The coating can optionally be applied to all of the substrate or spot printed on a certain portion. All such arrangements are understood herein as being "substantially contiguous."

Also, in the field of thermally-responsive record materials, there are well-known modifications in the coating structure. For example, a top-coating layer may be applied over a thermally-responsive layer as a protection for the latter, or a subcoating layer may be applied between the thermally-responsive layer and the support. Furthermore, some thermally-responsive record materials have both the topcoat and the subcoat in their design. The topcoat and subcoat may be either single-layered or multi-layered.

In manufacturing the record material, a coating composition is prepared which includes a fine dispersion of the components of the color-forming system, polymeric binder material, surface active agents and other additives in an aqueous coating medium. The composition can additionally contain inert pigments, such as clay, talc, aluminum hydroxide, calcined kaolin clay and calcium carbonate; synthetic pigments, such as urea-formaldehyde resin pigments; natural waxes such as Carnuba wax; synthetic waxes; lubricants such as zinc stearate; wetting agents; defoamers, and antioxidants. Other sensitizers can also be included. These sensitizers for example, can include acetoacetyl-o-toluidide, phenyl-1-hydroxy-2-naphthoate, 1,2-diphenoxyethane, and p-benzylbiphenyl or any of the sensitizing material listed earlier herein. Optionally, the record material can be topcoated or use subcoats such as insulating layers or hollow spheres. The color-forming system components are substantially insoluble in the dispersion vehicle (preferably water) and are ground to an individual average particle size of between about 1 micron to about 10 microns, preferably about 1-3 microns. The polymeric binder material is substantially vehicle soluble although latexes are also eligible in some instances.

Preferred water soluble binders include polyvinyl alcohol, hydroxyethylcellulose, methylcellulose, methyl(hydroxypropyl) cellulose, starch, modified starches, gelatin and the like. Eligible latex materials include polyacrylates, styrene-butadiene-rubber latexes, polyvinylacetates, polystyrene, and the like. The polymeric binder is used to
5 protect the coated materials from brushing and handling forces occasioned by storage and use of thermal sheets. Binder should be present in an amount to afford such protection in an amount less than will interfere with achieving reactive contact between color-forming reactive materials.

Coat weights can effectively be about 3 to about 9 grams per square meter
10 (gsm) and preferably about 5 to about 6 gsm. The practical amount of color-forming materials is controlled by economic considerations, functional parameters and desired handling characteristics of the coated sheets.

Electron-donating dye precursors are also known as compounds. These electron donating dye cursors or chromogens include chromogenic compounds such
15 as the phthalide, leucoauramine and fluoran compounds. These chromogenic materials or electron donating dye precursors are well known color-forming compounds for use in color-forming record systems. Examples of the compounds include Crystal Violet Lactone (3,3-bis(4-dimethylaminophenyl)-6-dimethylaminophthalide, (U.S. Patent No. RE 23,024); phenyl-, indolyl, pyrrolyl, and
20 carbazolyl-substituted phthalides (for example, in U.S. Pat. Nos. 3,491,111; 3,491,112; 3,491,116; 3,509,174); nitro-, amino-, amido-, sulfonamido-, aminobenzylidene-, halo-, anilino-substituted fluorans (for example, the U.S. Pat. Nos. 3,624,107; 3,627,78; 3,641,011; 3,642,828; 3,681,390); spirodipyranes (U.S. Pat. No. 3,971,808); and pyridine and pyrazine compounds (for example, in U.S. Pat.
25 Nos. 3,775,424 and 3,853,869). Other specifically eligible chromogenic compounds, not limiting the invention in any way, are: 3-diethylamino-6-methyl-7-anilino-flouran (U.S. Pat. No. 4,510,513); 3-dibutylamino-6-methyl-7-anilino-fluoran; 3-dibutylamino-7-(2-chloroanilino) fluoran; 3-(N-ethyl-N-tetrahydrofurfurylamino)-6-methyl-7-3,5'-tris(dimethylamino)spiro[9H-fluorene-9,1'(3'H)-isobenzofuran]-3'-one; 7-(1-ethyl-2-methylindole-3-yl)-7-(4-diethylamino-2-ethoxyphenyl)-5,7-dihydrofuro[3,4-b] pyridin-
30 5-one (U.S. Pat. No. 4,246,318); 3-diethylamino-7-(2-chloroanilino)fluoran (U.S. Pat. No. 3,920,510); 3-(N-methylcyclohexylamino)-6-methyl-7-anilino-fluoran (U.S. Pat. No. 3,959,571); 7-(1-octyl-2-methylindole-3-yl)-7-(4-diethylamino-2-ethoxyphenyl)-5,7-dihydrofuro[3,4-b]pyridin-5-one; 3-diethylamino-7,8-benzofluoran; 3,3-bis(1-ethyl-
35 2-methylindole-3-yl)phthalide; 3-diethylamino-7-anilino-fluoran; 3-diethylamino-7-

benzylaminofluoran; 3'-phenyl-7-dibenzylamino-2,2'-spirodi-[2H-1-benzopyran] and mixtures of any of the following.

Examples of eligible acidic developer material include the compounds listed in U.S. Pat. No. 3,539,375 as phenolic reactive material, particularly the monophenols and diphenols. Eligible acidic developer material also includes, without being considered as limiting, the following compounds which may be used individually or in mixtures: 4,4'-isopropylidinediphenol (Bisphenol A); p-hydroxybenzaldehyde; p-hydroxybenzophenone; p-hydroxypropiophenone; 2,4-dihydroxybenzophenone; 1,1-bis(4-hydroxyphenyl)cyclohexane; salicylanilide; 4-hydroxy-2-methylacetophenone; 2-acetylbenzoic acid; m-hydroxyacetanilide; p-hydroxyacetanilide; 2, 4-dihydroxyacetophenone; 4-hydroxy-4'-methylbenzophenone; 4,4'-dihydroxybenzophenone; 2,2-bis(4-hydroxyphenyl)-4-methylpentane; benzyl(4-hydroxyphenyl)ketone; 2,2-bis(4-hydroxyphenyl)-5-methylhexane; ethyl-4,4-bis(4-hydroxyphenyl) pentanoate; isopropyl-4,4-bis(4-hydroxyphenyl) pentanoate; methyl-4,4-bis(4-hydroxyphenyl) pentanoate; alkyl-4,4-bis(4-hydroxyphenyl) pentanoate; 3,3-bis(4-hydroxyphenyl) pentane; 4,4-bis(4-hydroxyphenyl) heptane; 2,2-bis(4-hydroxyphenyl)-1-phenylpropane; 2,2-bis(4-hydroxyphenyl) butane; 2,2'-methylene-bis(4-ethyl-6-tertiarybutyl phenol); 4-hydroxycoumarin; 7-hydroxy-4-methylcoumarin; 2,2'-methylene-bis(4-octyl phenol); 4,4'-sulfonyldiphenol; 4,4'-thiobis(6-tertiarybutyl-m-cresol); methyl-p-hydroxybenzoate; n-propyl-p-hydroxybenzoate; benzyl-p-hydroxybenzoate.

Preferred among these are the phenolic developer compounds. More preferred among the phenol compounds are 4,4'-isopropylidinediphenol, ethyl-4,4-bis(4-hydroxyphenyl)-pentanoate, n-propyl-4,4-bis(4-hydroxyphenyl)pentanoate, isopropyl-4,4-bis(4-hydroxyphenyl) pentanoate, methyl 4,4-bis(4-hydroxyphenyl) pentanoate, 2,2-bis(4-hydroxyphenyl)-4-methylpentane, p-hydroxybenzophenone, 2,4-dihydroxybenzophenone, 1,1-bis(4-hydroxyphenyl) cyclohexane, and benzyl-p-hydroxybenzoate. Acid compounds of other kind and types are eligible.

Examples of such other compounds are zeolites, phenolic novolak resins which are the product of reaction between, for example, formaldehyde and a phenol such as an alkylphenol, e.g., p-octylphenol, or other phenols such as p-phenylphenol, and the like; and acid mineral materials including colloidal silica, kaolin, bentonite, attapulgite, hallosyte, and the like. Some of the polymers and minerals do not melt but undergo color reaction on fusion of the chromogen.

The following examples are given to illustrate some of the features of the present and should not be considered as limiting. In these examples all parts or proportions are by weight and all measurement are in the metric system, unless otherwise stated.

5 In all examples illustrated in the present invention, a dispersion of a particular system component was prepared by milling the component in an aqueous solution of the binder until a particle size of between about 1 micron and 10 microns was achieved. The milling was accomplished in an attritor or other suitable milling device. The desired average particle size was about 1-3 microns in each dispersion.

10 Although some of the examples illustrate the invention using 2,2-bis (4-hydroxyphenyl)-4-methylpentane as the acidic developer material, the invention is readily practiced using any of the eligible acidic developer materials listed above.

The thermally-responsive sheets were made by making separate dispersions of chromogenic material, acidic material and the compound of formula I. The
15 dispersions were mixed in the desired ratios and applied to a support with a wire wound rod and dried. Other materials such as fillers, antioxidants, lubricants and waxes can be added if desired. The sheets may be calendered to improve smoothness.

The thermal images are measured using a McBeth RD-922 densitometer. The
20 densitometer is calibrated such that 0.08 indicates pure white and 1.79 a fully saturated black image.

Dispersions can be prepared in a quickie mill, attritor and small media mill. Optionally, but preferably dispersants can be added such as Nopco NDW at about 0.1 parts. This material is a sulfonated castor oil produced by Nopco Chemical
25 Company. Surfynol 104 which is a di-tertiary acetylene glycol surface active agent produced by Air Products and Chemicals, Inc. could also be included, for example at about 0.4 parts. Additionally, water-soluble polymers other than polyvinyl alcohol (PVA) may be used to prepare the dispersions.

Description of the Preferred Embodiments

30 In the following example, a general procedure is described for preparing compounds according to the invention. The examples are not intended to be exhaustive and the moieties, as previously defined, are all eligible for use in any combination in preparing the compounds. Unless otherwise noted, all measurements, percentages and parts are by weight.

SYNTHESIS EXAMPLE 1

Preparation of 2-(Benzyloxy)ethyl-[4-(benzyloxy)phenyl]ether (Compound A)

2-(Benzyloxy)ethanol (61.0g, 0.4 mole), and p-toluenesulfonyl chloride (80.0g, 0.4 mole) were added with stirring to acetonitrile (20 ml) in a litre, four-necked, round-bottom flask, equipped with a mechanical stirrer, reflux condenser, thermometer and a dropping funnel. Aqueous sodium hydroxide (40.0g, 1.0 mole/80 ml of water) was added slowly from the dropping funnel while the temperature of the reaction mixture was kept below 55°C. After the addition was complete, the reaction mixture was stirred for one hour as it cooled to room temperature. Then, 4-(benzyloxy)phenol (80.0g, 0.4 mole) was added and the reaction mixture (OV-1 column, 100°C for 2 minutes, 25°C/min to 300°C) showed that the reaction was complete.

The reaction mixture was poured into ice/water mixture and stirred. The precipitated solid was filtered and washed with cold water, dried and dissolved in toluene. The toluene solution was washed with aqueous sodium hydroxide (10%) and water, dried and concentrated. The crude product was dissolved in toluene solution was passed through a column of alumina using toluene as eluant. Fractions containing the product were collected, combined and concentrated. The residue was recrystallized from toluene/methanol. Yield: 97.2g (73%), white solid, M.P.: 73-75°C.)

ComponentsPartsDispersion A – Chromogenic Material

Chromogenic Material	32.0
25 Binder, 20% solution of Polyvinyl alcohol in water	27.4
Defoaming and dispersing agents	0.4
Water	40.2

Dispersion A1 – Chromogenic Material is ODB-2

30 3-Di(n-butylamino)-6-methyl-7-anilino-fluoran

Dispersion A1 – Chromogenic Material is ETAC

3-(N-Ethyl-N-p-tolylamino)-6-methyl-7-anilino-fluoran

Dispersion B – Acidic Material

Acidic Material	42.5
Binder, 20% solution of Polyvinyl alcohol in water	21.2
Defoaming and dispersing agents	36.1

5

Dispersion B1 – Acidic Material is AP-5

2,2-Bis(4-hydroxyphenyl)-4-methylpentane

Dispersion B2 – Acidic Material is TGSA

10 Bis(3-allyl-4-hydroxyphenyl)sulfone

Dispersion C – Sensitizing Material

Sensitizing Material	42.5
Binder, 20% solution of Polyvinyl alcohol in water	21.2
15 Defoaming and dispersing agents	0.2
Water	36.1

Dispersion C1 – Sensitizing Material is DMT

Dimethyl terephthalate

20

Dispersion C2 – Sensitizing Material is pBBP

p-Benzylbiphenyl

Dispersion C3 – Sensitizing Material is stearamide wax

25

Dispersion C4 – Sensitizing Material is BZLPE-3

2-(Benzyloxy)ethyl-[4-(benzyloxy)phenyl]ether (compound A)

	<u>Coating Formulation 1</u>	<u>Parts</u>
30	Dispersion A (Chromogenic)	7.6
	Dispersion B (Acidic)	15.0
	Dispersion C (Sensitizing)	15.0
	Binder, 10% solution of polyvinylalcohol in water	45.5
	Filler slurry, 50% in water	19.0

35

EXAMPLE 1

- Coating Formulation 1 Using
Dispersion A1 (ODB-2)
Dispersion B1 (AP-5)
5 Dispersion C4 (BZLPE-3)

EXAMPLE 2

- Coating Formulation 1 Using
Dispersion A2 (ETAC)
10 Dispersion B1 (AP-5)
Dispersion C4 (BZLPE-3)

EXAMPLE 3

- Coating Formulation 1 Using
15 Dispersion A1 (ODB-2)
Dispersion B2 (TGSA)
Dispersion C4 (BZLPE-3)

EXAMPLE 4

- Coating Formulation 1 Using
20 Dispersion A2 (ETAC)
Dispersion B2 (TGSA)
Dispersion C4 (BZLPE-3)

COMPARATIVE EXAMPLE 1

- 25 Coating Formulation 1 Using
Dispersion A1 (ODB-2)
Dispersion B1 (AP-5)
Dispersion C1 (DMT)

30 COMPARATIVE EXAMPLE 2

- Coating Formulation 1 Using
Dispersion A2 (ETAC)
Dispersion B1 (AP-5)
Dispersion C1 (DMT)

35

COMPARATIVE EXAMPLE 3

- Coating Formulation 1 Using
Dispersion A1 (ODB-2)
Dispersion B1 (AP-5)
5 Dispersion C2 (pBBP)

COMPARATIVE EXAMPLE 4

- Coating Formulation 1 Using
Dispersion A2 (ETAC)
10 Dispersion B1 (AP-5)
Dispersion C2 (pBBP)

COMPARATIVE EXAMPLE 5

- Coating Formulation 1 Using
15 Dispersion A1 (ODB-2)
Dispersion B1 (AP-5)
Dispersion C3 (stearamide wax)

COMPARATIVE EXAMPLE 6

- 20 Coating Formulation 1 Using
Dispersion A2 (ETAC)
Dispersion B1 (AP-5)
Dispersion C3 (stearamide wax)

25 COMPARATIVE EXAMPLE 7

- Coating Formulation 1 Using
Dispersion A1 (ODB-2)
Dispersion B2 (TGSA)
Dispersion C1 (DMT)

30

COMPARATIVE EXAMPLE 8

- Coating Formulation 1 Using
Dispersion A2 (ETAC)
Dispersion B2 (TGSA)
35 Dispersion C1 (DMT)

COMPARATIVE EXAMPLE 9**Coating Formulation 1 Using****Dispersion A1 (ODB-2)****5 Dispersion B2 (TGSA)****Dispersion C2 (pBBP)****COMPARATIVE EXAMPLE 10****Coating Formulation 1 Using****10 Dispersion A2 (ETAC)****Dispersion B2 (TGSA)****Dispersion C2 (pBBP)****COMPARATIVE EXAMPLE 11****15 Coating Formulation 1 Using****Dispersion A1 (ODB-2)****Dispersion B2 (TGSA)****Dispersion C3 (stearamide wax)****20 COMPARATIVE EXAMPLE 12****Coating Formulation 1 Using****Dispersion A2 (ETAC)****Dispersion B2 (TGSA)****Dispersion C3 (stearamide wax)****25****Coating Formulation 2****Parts****Dispersion A (Chromogenic)****7.6****Dispersion B (Acidic)****15.0****Dispersion C (Sensitizing)****0.0****30 Binder, 10% solution of polyvinylalcohol in water****45.5****Filler slurry, 50% in water****19.0**

COMPARATIVE EXAMPLE 13

Coating Formulation 2 Using

Dispersion A1 (ODB-2)

Dispersion B1 (AP-5)

5

COMPARATIVE EXAMPLE 14

Coating Formulation 2 Using

Dispersion A2 (ETAC)

Dispersion B1 (AP-5)

10

COMPARATIVE EXAMPLE 15

Coating Formulation 2 Using

Dispersion A1 (ODB-2)

Dispersion B2 (TGSA)

15

COMPARATIVE EXAMPLE 16

Coating Formulation 2 Using

Dispersion A2 (ETAC)

Dispersion B2 (TGSA)

20

The examples were coated at 3.0gm/m^2 . A PVA topcoat was applied at 3.5gm/m^2 .


The examples were then printed on the ATLANTTEK model 300. The optical density was measured using a McBeth II densitometer. The results are in the following chart.

Example #	McBeth Intensity at 12.0mj/mm ²	McBeth Intensity at 31.8mj/mm ²
1	0.56	1.38
2	0.26	1.30
3	0.99	1.44
4	0.73	1.40
Comparative 1	0.23	1.40
Comparative 2	0.10	1.30
Comparative 3	0.28	1.40
Comparative 4	0.11	1.01
Comparative 5	0.31	1.39
Comparative 6	0.10	1.43
Comparative 7	0.44	1.43
Comparative 8	0.18	1.32
Comparative 9	0.36	1.42
Comparative 10	0.27	1.33
Comparative 11	0.52	1.43
Comparative 12	0.17	1.14
Comparative 13	0.20	1.28
Comparative 14	0.11	0.96
Comparative 15	0.32	1.36
Comparative 16	0.11	0.83

The principles, preferred embodiments, and modes of preparation the present invention have been described in the foregoing specification. The invention which is intended to be protected herein, however, it is not to be construed as limited to the particular forms disclosed, since these are to be regarded as illustrative rather than restrictive. Variations and changes can be made by those skilled in the art without departing from the spirit and scope of the invention.


We claim:

1. A thermally-responsive record material comprising a substrate having provided thereon in substantially contiguous relationship an electron donating dye precursor, an acidic developer material, a compound of the formula:




wherein P is selected from

10



and



;

wherein R₁, R₂, and R₃ are each independently selected from hydrogen, alkyl, alkoxy, aryl, aralkyl, aralkoxy, halogen, and alkoxyalkoxy,

15

wherein R₄ is independently selected from alkoxyalkyl, alkoxyalkoxy and aralkoxyalkoxy,

20


said alkyl moieties each independently being from one to eight carbons, said aryl moieties each independently being unsubstituted or substituted by alkyl (C₁-C₈), alkoxy (C₁-C₈) or halogen,

and a suitable binder therefor.

2. A thermally-responsive record material comprising a substrate having provided thereon in substantially contiguous relationship an electron donating dye precursor, an acidic developer material, a compound of the formula:

5

(II)



wherein R₁, R₂, and R₃ are each independently selected from hydrogen, alkyl, alkoxy, aryl, aralkyl, aralkoxy, halogen, and alkoxyalkoxy,

10


wherein R₄ is independently selected from alkoxyalkyl, alkoxyalkoxy and aralkoxyalkoxy,

said alkyl moieties each independently being from one to eight carbons, said aryl moieties each independently being unsubstituted or substituted by alkyl ((C₁-C₈)), alkoxy (C₁-C₈) or halogen,


15

and a suitable binder therefor.


3. The thermally-responsive record material according to claim 2 wherein the compound according to formula II is



4. The thermally-responsive record material according to claim 2 wherein the compound according to formula II is




5. The thermally-responsive record material according to claim 2 wherein the compound according to formula II is



6. A thermally-responsive record material comprising a substrate having provided thereon in substantially contiguous relationship an electron donating dye precursor, an acidic developer material, a compound of the formula:

(III)

5



wherein R₁ and R₂ and R₃ are each independently selected from hydrogen, alkyl, alkoxy, aryl, aralkyl, aralkoxy, halogen, alkoxyalkoxy and aralkoxyalkoxy,

10


wherein R₄ is independently selected from alkoxyalkyl, alkoxyalkoxy and aralkoxyalkoxy,

said alkyl moieties each independently being from one to eight carbons, said aryl moieties each independently being unsubstituted or substituted by alkyl (C₁-C₈), alkoxy (C₁-C₈) or halogen,


15

and a suitable binder therefor.


7. The thermally-responsive record material according to claim 6, wherein the compound according to formula III is




8. The thermally-responsive record material according to claim 6, wherein the compound according to formula III is




9. The thermally-responsive record material according to claim 6, wherein the compound according to formula III is




10. The thermally-responsive record material according to claim 6, wherein the compound according to formula III is




11. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




12. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




13. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




14. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




15. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is



16. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




17. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




5


18. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




19. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




20. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




21. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




22. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is




23. The thermally-responsive record material according to claim 3 wherein the compound according to formula III is



24. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is



25. The thermally-responsive record material according to claim 6 wherein the compound according to formula III is



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/34473

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) :B41M 5/20, 5/24

US CL :503/209

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 503/209, 200, 208, 216

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5,841,196 A (SCHULTZ et al.) 13 October 1998, see entire document.	1-25
A	US 5,955,398 A (FISHER et al.) 21 September 1999, see entire document.	1-25
A	US 6,015,771 A (FISHER et al.) 18 January 2000, see entire document.	1-25

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

08 FEBRUARY 2001

Date of mailing of the international search report

01 MAR 2001

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

ELIZABETH EVANS

Telephone No. (703) 308-0661

Jean Proctor
Paralegal Specialist